



# Rubcoat VP

Vapour Proof for mushroom cells.

# RUBCOAT

## SPECIAL COATINGS

**Ready-to-use elastic sealant for mushroom cells. To be used on dry substrates.  
Based on a high-quality acrylic co-polymer. Solvent free.**

### Product properties

Rubcoat contains no solvents. Once hardened, it remains permanently elastic and temperature resistant. Rubcoat VP is resistant to a large number of acids and chemicals. Rubcoat VP is extremely elastic, possesses excellent adhesion and is virtually maintenance-free.

### Technical data

Basis	: synthetic dispersion
Packing	: 23 kg bucket
Solvent	: none
Color	: white
Consistency	: semi-liquid paste
Density	: 1.165
VOC level	: 0 gr / liter.
Application	: roller or brush Airless sprayer 0.21 to 0.25
Application temp.	: +5 °C to +30 °C
Pre-treatment	: Rubcoatprimer
Temp. resistance	: -20 °C to +80 °C
Elasticity	: ISO 1519 > 90%
Consumption	: 2 kg/m <sup>2</sup>
Mu value	: > 78.000
Cleaning material	: water

### Application

Elastic sealant for a gas and vapour-proof finish on walls and ceilings in mushroom cells and climate rooms.

### How to apply

The substrate must be solid, dry and clean of oil and grease. Only apply the product above 5 °C and if the moisture content of the surface is less than 15%. Pre-treat porous substrates with Rubcoat primer. Drying time 1-3 hours. Pre-treat smooth substrates with Rubcoat primer KS. Drying time 3-6 hours. Apply Rubcoat VP in at least 2 layers with a total consumption of 2 kg/m<sup>2</sup>. Strengthen joints and gaps with Rubcoat polyester film.

### Supply and storage

Rubcoat VP is supplied in 23 kg buckets. The product has a shelf life of 2 years if the package is unopened and the storage temperature is between 5 °C and 25 °C.

### Transport data

Transport via:  
road - ADR free  
sea - IMDG free  
air - ICAO/IATA-DRG free  
UN-nr - not applicable

### Remarks

We draw your attention to the fact that this information sheet cancels all previous information about this product. We retain the right to make changes in the event of technical progress.



RUBCOAT® is a trademark of Rubcoat B.V.

Correspondence address: P.O. Box 2086, 6020 AB Budel (NL) • Visitor's address: 't Inne 32c, 6021 DA Budel (NL)  
Tel. : +31 495 49 19 16 • Fax : +31 495 49 37 50 • info@rubcoat.com • www.rubcoat.com

