



# Rubcoat VPX

*Vapour Proof Extra sealant for compost tunnels*

# RUBCOAT

**SPECIAL COATINGS**

**Ready-to-use elastic sealant for compost tunnels. To be used on dry substrates.  
Based on a high-quality Acrylic Co-polymer. Solvent-free.**

## Product properties

Rubcoat VPX contains no solvents. Once hardened, it remains permanently elastic and temperature resistant. Rubcoat VPX is resistant to ammonia and a large number of acids and chemicals. Rubcoat VPX is extremely elastic, possesses excellent adhesion and is virtually maintenance-free.

## Technical data

Basis	: synthetic dispersion
Packing	: bucket 23 kg
Solvent	: none
Colour	: white
Consistency	: semi liquid pasta
Density	: 1,165
Application	: roller of brush airless sprayer nozzle 0,21 tot 0,28
Fire resistance	: DIN 4102 norm B1 standard
Application temp.	: 5 °C tot 30 °C
Pre-treatment	: Rubcoatprimer
Temp. resistance	: -40 °C tot + 90 °C
Elasticity	: ISO 1519 > 90%
Consumption	: 2 kg/m <sup>2</sup>
UV resistance	: DIN 18363 Nr 2.4.2.1 A1 standard
Mu value	: > 330.000
Cleaning material	: water

## Applications

Elastic sealant for a gas and vapour-proof finish on walls and ceilings in compost tunnels.

## How to apply

The substrate must be solid, dry and clean and free of oil and grease. Only apply the product above 5 °C and if the moisture content of the surface is less than 15%.

Pre-treat porous substrates with Rubcoat primer. Drying time 1-3 hours.

Pre-treat smooth substrates with Rubcoatprimer KS. Drying time 3-6 hours.

Apply Rubcoat VPX in at least 2 layers with a total consumption of 2 kg/m<sup>2</sup>.

## Supply and storage

Rubcoat VPX is supplied in 23 kg buckets. The product has a shelf life of 2 years if the package is unopened and the storage temperature is between 5 °C and 25 °C.

## Transport data

Transport via:  
road - ADR free  
see - IMDG free  
air - ICAO/IATA-DRG free  
UN-nr - not applicable

## Remarks

We draw your attention to the fact that this information sheet cancels all previous information about this product.

We retain the right to make changes in the event of technical progress.



**RUBCOAT® is a trademark of Rubcoat B.V.**

**Correspondence address:** P.O. Box 2086, 6020 AB Budel (NL) • **Visitor's address:** 't Inne 32c, 6021 DA Budel (NL)  
Tel. : +31 495 49 19 16 • Fax : +31 495 49 37 50 • [info@rubcoat.com](mailto:info@rubcoat.com) • [www.rubcoat.com](http://www.rubcoat.com)

